PTO 01-1178

AIR-CLEANING FILTER ELEMENT [Kuki joka firuta- eremen'to]

Mamoru Kitajima, et al.

UNITED STATES PATENT AND TRADEMARK OFFICE Washington, D.C. February 2001

Translated by: FLS, Inc.

PUBLICATION COUNTRY	(10):	JP
DOCUMENT NUMBER	(11):	04074505
DOCUMENT KIND	(12):	A
PUBLICATION DATE	(43):	19920309
PUBLICATION DATE	(45):	
APPLICATION NUMBER	(21):	02185492
APPLICATION DATE	(22):	19900714
ADDITION TO	(61):	
INTERNATIONAL CLASSIFICATION	(51):	
DOMESTIC CLASSIFICATION	(52):	B01D 39/14; B01D 46/52; B01D 53/04; B01D 53/34
PRIORITY COUNTRY	(33):	
PRIORITY NUMBER	(31):	
PRIORITY DATE	(32):	
INVENTOR	(72):	KITAJIMA, MAMORU, ET AL.
APPLICANT	(71):	KURARAY CHEMICAL CORP.
TITLE	(54):	AIR-CLEANING FILTER ELEMENT
FOREIGN TITLE	[54A]:	KUKI JOKA FIRUTA- EREMEN'TO

Title of the Invention
 Air-cleaning filter Element

2. Claims

An air-cleaning filter element comprised by laminating a sheet-like electret filter with a sheet containing an offensive odor adsorbent, and integrally molding them in a pleated shape.

3. Detailed Specifications

(Field of Industrial Utilization)

The present invention pertains to a filter element used in air purifiers. It has a function for collectively removing the dust and offensive odors floating in the air, but in particular, the performance of the filter element is such that the pressure loss is low and the purifying effect is high.

(Prior Art)

In order to remove dust floating in the air, electrostatic air purifiers or electric dust collectors were used in the past. They charged dust particles using corona discharge and collected and removed these particles using an electrode or filter with the opposite charge. However, besides the fact that a high voltage of several KV to several tens of KV was required in order to charge the dust particles by corona discharge, and there were risks from a handling standpoint, there was fear that a fire could occur. Thus, the demand for a dust collector that did not

^{*}Number in the margin indicates pagination in the foreign text.

require a high voltage was strong. Various filters also had been proposed regardless of the electrostatic merits. However, it is often the case that cigarette smoke was present and it was necessary to also collect the dust in the air inside rooms and cars with a diameter of 1 µm diameter or less. In order to remove these kinds of microscopic particles by filtration, the need for a filter with an extremely high pressure loss was unavoidable. Consequently, it was extremely difficult to remove the fine dust particles in this system with good efficiency at a low pressure loss.

Thus, a low pressure loss type air-cleaning filter with a combined honeycomb sheet containing activated carbon and an electret filter is disclosed in Tokkai No. 58-175560.

In order to remove offensive odors in the air, a layer packed with activated carbon primarily was used in filters in the past. However, the adsorption rate of the malodorous substances was slow. In order to improve this, an air filter with a small activated carbon particle size was used, or a filter with a thicker packing layer was used. However, the pressure loss increased with this kind of construction. In addition, the noise from the fan became a problem if an adequate air capacity was maintained.

Furthermore, the ability of activated carbon to adsorb and remove various malodorous substances extensively is outstanding, but the capacity to adsorb ammonia or the main constituents of offensive cigarette odors—acetaldehydes—indoors is inadequate.

In addition, a method in which an electret filter and a material in which a fine activated carbon powder or other adsorbent is adhered to a urethane foam were combined, a method in which an electret filter and a filter in which a fibrous activated carbon was made into paper and then into the form of a sheet, and subsequently into the form of a filter by corrugation and lamination, among other methods, are used as methods for removing both dust and offensive odors in the air. However, there were many problems because the life span of the activated carbon-containing filter was shorter than the electret filter. (Problems Which the Invention Intends to Solve)

When electret filters and deodorizing sheets were used together, they were often used by combining an electret filter formed in a pleated shape and a deodorizing sheet formed in a flat shape. The pleats in the electret filter were good for reducing the pressure loss when the air capacity was high. And in order to improve the adsorption capacity, the life span of the deodorizing sheet containing the adsorbent was considered, and it was placed on the front face or rear face of a pleated electret filter whose sheet thickness was increased to a certain degree. In order to lengthen the deodorizing life span, it was necessary to increase the amount of adsorbent. The situation was that the thickness of the adsorbent layer increased, the air passageway narrowed, and a rise in the pressure loss was not avoided.

(Means Used to Solve the Problems)

The inventors of the present invention investigated a method in which fine activated carbon particles were used as an adsorbent and they were adhered to the surface of a textile or web, and furthermore, the relationship between the adsorption capacity and pressure loss when the filter obtained in this way and an electret filter were molded integrally in a pleated shape. As a result, in integrally molding a filter in which fine activated carbon particles were impregnated in the surface of a textile or web with an adhesive in the shape of pleats, they discovered that it was possible for the impregnated amount of adsorbent to be higher than in the past without the pressure loss rising as much, and they arrived at the present invention based on that.

That is, it is an air-cleaning filter element comprised by laminating a sheet-like electret filter and a sheet containing an offensive odor adsorbent, and integrally molding them in a pleated shape.

The present invention will be explained in detail below.

The texture of the sheet-like electret filter used in the present invention is not especially limited, but when it is utilized in an air purifier, it is often used in a state in which the air capacity is considerably high. It is necessary to keep the pressure loss low even under that kind of condition.

Consequently, a nonwoven fabric with a coarse texture is suitable for the filter. It is necessary that the material be one in

which it can be subjected to an electret processing and pleated using heat. For example, synthetic fibers, such as polyvinylidene fluoride, polypropylene, polyethylene and polyester fibers, are suitable.

The material of the electret filter is polarized electrically. In other words, the surface is in a state in which it always has a fixed electrostatic charge. Consequently, the surface of the electret filter is charged with negative electricity, and microscopic particles, such as cigarette smoke with a diameter of 1 µm or less and having the usual positive charge, are sucked into and removed through a section of the electret filter having a negative charge. Thus, fine particles can be removed with good efficiency at a low pressure loss. Removing these kinds of microscopic particles in the usual filtering method is considerably difficult. In addition, the pressure loss cannot help from becoming extremely high and the dominant properties of the electret filter are extremely marked.

An electret filter normally is fabricated by subjecting a polarized material that is serving as dielectric and a polymer, such as polyester or polypropylene, to an electret treatment. Various methods are known as electret treatment methods in which polarization is done permanently, but normally, a method in which the dielectric is interposed between electrode plates, the temperature is elevated to just under the softening point, and annealed close to room temperature when a high DC voltage is applied. In addition, this polarized state continues for several

years; hence, the filter has a function for removing microscopic particles over a long period of time. Moreover, it is not necessary to apply a high voltage when it is in use; hence, it is handled with ease, there is no danger of a fire occurring, and it is highly safe.

The offensive odor adsorbent is not especially limited, but it is necessary that it have performance for removing offensive odors in the air; activated carbon, zeolite, essential vegetable oils, and the like are effective. In particular, activated carbon is a unique material having an extremely outstanding adsorption capacity as a nonpolar adsorbent. It exhibits a high adsorption capacity on almost all gaseous substances; hence, it is extremely outstanding.

Any coconut husk-based, charcoal-based, or coal-based activated carbon may be used for the activated carbon.

In addition, the effect of the grain size of the activated carbon on the adsorption rate of the malodorous components is extremely large. The smaller the grain size, the faster the adsorption rate. As shown in this practical example, it is an activated carbon with coconut husk as the raw material, and a 300 mesh path of 90% and an average particle size of about 20 μ m are suitable.

The material composing the sheet containing the adsorbent is not especially limited, but it is necessary that it be disposed to being pleatable. As for the structure of the sheet, webs, textiles, nonwoven fabrics, nets, and the like can be used

diversely. For example, polyester, polypropylene, nylon, and the like are suitable for materials able to be pleated. In addition, the weaving or knitting methods are not limited, but in order to reduce resistance to ventilation, a mesh-like cloth formed with holes in specified intervals is preferable.

The method by which the activated charcoal particles are contained in a sheet is not especially limited, but a binder is necessary in order to impregnate them in the fibers of a web, etc. However, some of the surface of the activated carbon is covered by the binder; hence, it is difficult to avoid a reduction in the adsorbing capacity to a certain degree, but the extent of the reduction differs depending on the type of activated carbon thereof. Generally, if a latex-based adsorbent having suspended particles with a large particle size is used, it is confirmed that the extent of the reduction in the adsorbing capacity is small.

The fine activated carbon particles can be impregnated in the fiber surface of the web or the like by dispersing the fine activated carbon particles in a latex, dipping the aforementioned web or the like in that, and lightly squeezing and drying it.

It is necessary to integrally mold the filter element of the present invention in a pleated shape by laminating the electret filter and the adsorbent-containing filter.

It can be molded integrally by pleating it at the time it is laminated. A solid integral molding is possible when a small amount of hot-melt adhesive is used as well.

Pleating may be carried out in a method such as making folds and then passing this between hot plates. On that occasion, it is preferable to simultaneously overlap and pleat the electret filter and the sheet impregnated with the adsorbent or activated carbon. In addition, in order to inhibit the electret filter and sheet to which the adsorbent or activated carbon is adhered from shifting, a method, such as spot-bonding both sheets with a hotmelt or other kind of adhesive also can be applied.

After separately pleating them, they may be used by adhering them. In addition, they may be used by overlapping the electret sheet on both the front and back sides of the sheet to which the adsorbent or activated carbon was adhered, or by laminating them.

In order to prevent the shape from collapsing after pleating, the top of each crest may be linked with a polymer material or other reinforcing agent so that the pitch of the pleats is not disordered.

The present invention is a filter element used in air purifiers. As stated above, the integrally molded filter is installed by cutting it into the desired size according to the size of the air purifier. The air purifier is not especially limited and air purifiers used for inside rooms of office buildings, for homes, inside cars, and the like are diversely included.

(Effects and Merits)

The present invention is such that in addition to dust with a 1 µm diameter or less floating in the air, which is the main

constituent of violet cigarette smoke in the air, offensive odors in the air may be removed with good efficiency by combining the electret filter and the activated carbon sheet.

In addition, because the filter has a characteristic in which the pressure loss is extremely low, it is suited to circulating a large amount of air and it is suitable in filter elements for air purifiers.

Furthermore, this laminated filter is molded integrally; hence, it is compact, it is handled with ease, and it also is suitable as a filter element for air purifiers accordingly.

(Practical Examples)

The present invention will be explained more specifically below by citing practical examples.

Filter elements prepared by using the following elements ${\bf a}$, ${\bf b}$ and ${\bf c}$ were used in the practical examples of the present invention.

Element a: an electret filter

Material: polypropylene, fiber diameter: 30 µm

Thickness: 1 mm, basis weight: 100 g/m²

Pleat width: 1 cm, number of pleat crests per cm: 1, length behind pleat: 1/2 the original length

Element \mathbf{b} : a sheet with activated carbon powder adhered to netlike web

The material and shape of the net-like web include a web knitted with stitches spread 3 mm and a 50 g/m^2 basis weight by using 100 dr polyester yarn.

100 parts fine coconut husk activated carbon particles having the usual adsorbing capacity were dispersed in 120 parts water, a suspension in which 40 parts of a 2% CMC aqueous solution and 260 parts of a 45% acrylonitrile butadiene-based latex were added was prepared as the adhesive, the abovementioned net-like web was dipped in the suspension, lifted out, and subsequently squeezed and dried at 120°C.

Element \mathbf{c} : a sheet-like activated carbon using a polyurethane foam sheet

A cell-venting product of a polyurethane foam sheet (number of cells per inch: 8, thickness: 3 mm, polyurethane basis weight: $80~g/m^2$) was dipped in the same activated carbon suspension as for the sample ${\bf b}$, squeezed so that the activated carbon basis weight was $150~g/m^2$, and subsequently dried at $120\,^{\circ}{\rm C}$.

Practical Example 1

The element **a** was pleated at the same thickness as the element **b**, and the element **a** and element **b** were spot-bonded and laminated with a small amount of hot-melt adhesive.

A perspective view thereof is shown in Fig. 2. In addition, the weight per unit area of activated carbon and the pressure loss of the element are shown in Table 1.

The weight per unit area of activated carbon was measured according to JIS M 8812 (method for industrially analyzing types of carbon and coke), and the pressure loss was measured at an air capacity of 1 m/sec at $25\,^{\circ}$ C.

The adsorbing ability of the element is shown in Fig. 1. The adsorbing ability was shown according to the relationship between the operating time of air purifying device and the remaining percentage of the hydrogen sulfide gas. The measurement method thereof is as stated below.

An element cut to 10 cm×30 cm was installed in an air purifying device able to treat gas at a 1 m/sec air capacity, and set inside a 1 m³ acrylic box with the hydrogen sulfide gas concentration pre-adjusted to 1,000 ppm. The relationship between the air circulation time and the residual hydrogen sulfide gas concentration was examined. The results thereof are shown in Fig. 1.

During the gas concentration measurement, a highly sensitive gas chromatograph equipped with an FPD detector (flame ionization detector) was used.

The element was installed in an air purifying device, the atmosphere was suctioned, and the atmospheric dust-removing ability on the discharge side examined. However, a difference with the element **a** was not confirmed.

Comparative Example 1

The element **c** was placed behind the element **a** to make an element. The relationship between the activated carbon basis weight and the pressure loss of the element, and the relationship between the operating time of air purifying device and the remaining percentage of the hydrogen sulfide gas were measured in the same manner as in Practical Example 1. The results thereof

are shown in Table 1 and Fig. 1.

Comparative Example 2

An unpleated element **b** was placed behind the element **a** to make an element. The relationship between the activated carbon basis weight and the pressure loss of the element, and the relationship between the operating time of air purifying device and the remaining percentage of the hydrogen sulfide gas were measured in the same manner as in Practical Example 1. The results thereof are shown in Table 1 and Fig. 1.

Table 1

<u>/29</u>

	Practical Example 1	Comparative Example 1	Comparative Example 2
Total weight per unit area g/m	500	430	400
Activated carbon weight per unit area g/m	200	150	100
Pressure loss mmÅq/sheet	0.9	1.0	1.0

4. Brief Description of the Figures

Figure 1 shows the relationship between the operating time of an air purifying device and the remaining percentage hydrogen sulfide gas in Practical Example 1 and Comparative Examples 1 and 2.

- 1: Practical Example 1
- 2: Comparative Example 1
- 3: Comparative Example 2


Figure 2 shows an embodiment of the present invention in a perspective view of an offensive odor element by overlapping a filter in which activated carbon was adhered to a net-like web

and an electret sheet.


- 4: activated carbon impregnated sheet
- 5: electret filter

[Figure 1]

Key: (a) Operating time of air purifying device; (b) Remaining percentage of $\rm H_2S$ gas; (c) minutes



第 2 🕱 [Figure 2]



◎ 公 開 特 許 公 報 (A) 平4-74505

ᢒint. Cl. 5	識別記号	庁内整理番号	@公開	平成4年(1992)3月9日
B 01 D 39/14	B F	7059-4D 7059-4D		
46/52 53/04 53/34	A 116 J	7059-4D 8616-4D 6953-4D 棄本報句	◇ 李護士 3	豊文項の数 1 (全6頁)

60発明の名称 空気浄化フィルターエレメント

②特 願 平2-185492 ②出 願 平2(1990)7月14日

@発 明 者 北 島 衛 岡山県岡山市福島3丁目12-40

回発 明 者 岡 田 輝 弘 岡山県備前市鶴海3111 回出 顧 人 クラレケミカル株式会 岡山県備前市鶴海4342

21

個代 理 人 弁型士, 小田中 壽雄

明 細 鸖

I. 発明の名称

空気浄化フィルターエレメント

2 特許請求の範囲

シート状のエレクトレットフィルターと、 駆臭 の吸着剤を含有するシートを報回し、 ブリーツ状 に一体成形せしめてなる空気浄化フィルターエレ メント。

3. 発明の詳細な説明

(産業上の利用分野)

本発明は、空気清浄機に使用するフィルターエレメントに関するものである。空気中に浮遊する粉じんと悪臭を併せて除去する機能を有するが、特に、圧損失が低く、しかも荷浄効果が高い性能を持ったフィルターエレメントである。

〔従来の技術〕

従来、空気中の浮遊粉じんを除去するためには 静電空気清浄機、或いは電気楽じん機が使用され ていた。これらはコロナ放電により粉じんの粒子 を帯電させ、この粉子を反対の電荷を有する電板 またはフィルターにより補集除去するものである。しかし、コロナ放電により、初じん粒子を荷電するためには放KV或いは数10KVの高電圧が必要となり、取扱上危険があるのみならず、火災が発生するおとしん装置しないのである。このため高離圧を必要にないませんというなどは、たいないないない。このおりには、このようなには、からないない。このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このようなでは、このが表することは、この方を除去することは極めて困難であった。

このため特別昭58-175560 号公報には活性度を合むハニカム型シートとエレクトレットフィルターを組み合わせた低圧損失型空気浄化用フィルターが訊示されている。

空気中の展臭を除去するために、従来主として フィルターに活性炭充填層が使用されていたが、 駆臭物質の吸着速度がおそいのでこれを改善するため、活性炭の粒差が小さいものを使用するか、または充壌層を厚くしたものが使用された。しかし、このような構造にすると圧損失が増大し、また充分な風量を確保しようとするとファンの騒音が問題となった。

更に、活性炭はかなり広範囲にわたり種々の展 臭物質を吸剤除去する能力がすぐれているが、ア ンモニア改いは室内のたばこの臭気の主成分であ るアセトアルデヒドの吸着性が不充分である。

また、空気中の粉じんと悪臭の両者を除去する方法として、エレクトレットフィルターとウタンフォームに粉末状活性炭または他の吸着剤を付着させたものとを併用する方法、エレクトレットフィルターと繊維状活性炭を抄紙して紙状とした後、コルゲーション加工・積層によりフィルター形状にしたものとを併用する方法等が使用されている。しかし、エレクトレットフィルターに対して活性食育フィルターの野命が短い等多くの問題があった。

- 3 -

使用し、吸着剤の細物又は繊物の裏面への接着方法、更に、このようにして得られたフィルターを エレクトレットフィルターをブリーツ状に一体成形した場合の吸着を最と旺損失の関係について 野した。その結果、活性炭酸粉末を接着剤で顕物 又は繊物の裏面に添着したフィルターとエレクト レットフィルターをブリーツ状に一体成形した。 では、圧損失がそれ程上昇せずに吸着剤の添着が を従来より多くできることを見出し、それに基づいて本発列に到達した。

「すなわち、シート状のエレクトレットフィルターと、悪臭の吸着剤を含有するシートを積層し、 ブリーツ状に一体成形せしめてなる空気浄化フィ ルターエレメントである。

以下、本苑明について詳しく説明する。

本発明に使用するシート状のエレクトレットフィルターの超離は特に限定しないが、空気精浄機に使用する場合は流速がかなり高い状態で使用されることが多く、そのような条件においても、圧損失を低く抑える必要がある。従って、フィルタ

[発明が解決しようとする鞣ಟ]

従って、空気精節機用として浮遊粉じんと悪具 の両成分を除去できるフィルターで、寿命が長く、 圧損失が少なく且つコンパクトな形状で取扱易い フィルターエレメラトが要望されていた。

(問題点を解決するための手段)

水発明者等は、吸着剤として、活性炭酸粉末を

- 4 -

ーは担な組織の不織布が遊している。材質は、エレクトレット加工と、熱によるプリーツ加工の出 来るものである必要があり、例えば、ポリ那化ビニリデン、ポリプロビレン、ポリエチレン、ポリ エステルなどの合成職継が好適である。

エレクトレットフィルターは材質が電気的に分をされていて、検言すれば、表面では、でいる。従って、状態となっている。従うを帯でした状態とのの表面に負なを帯が出来した。では、エさ以レーの負債を存すする。この負債がある。この負債がある。このでは、は、またによるで、よりで、よりでは、は、またによるをは、は、またによるをは、またによるをは、またには、またといりに、なることは、またに、なることは、またに、なることは、またに、スルターの便位性をある。

エレクトレットフィルターは通常、分極化して 誘電体となる材質、例えばポリエステル、ポリブ ロピレン等のポリマーをエレクトレット処理する ことにより作られる。永久的に分極化するエレクトレット処理法として、種々の方法が知られているが、通常誘電体を電極板にはさみ軟化点付近室昇温し、直流高電圧を加えた状態で窒温迄徐冷する方法が採用されている。またこの分極状態は対応されるため長期間にわたって震微粒子除去機能を有する。しかも、使用する場合高電形をかける必要がないので、取扱が容易で火災を発生する危険がなく、安全性が高い。

悪臭の吸着剤はとくに限定しないが、空気中の 悪臭を除去する性能を有するものである必要があ り、活性炭、ゼオライト、植物精油等が有効であ る。特に、活性炭は無極性吸着剤として極めて優 れた吸着性を有する特異な材質で、殆ど全てのガ ス状物質に対して高い吸着性を示すため、最も優 れている。

括性炭は、ヤン殻系でも、木炭系でも又は石炭 系のものの何れでも使用可能である。

また活性炭の粒度が悪臭成分の吸着速度に及ぼ す影響は非常に大きく、粒度が小さいほど吸着速

- 7 -

使用すると、吸着能力低下の反合いが小さいこと が認められる。

このようなラテックスに括性炭酸粒子を分散させ、その中に前記の類物等を浸漬し、かるく絞って乾燥させることにより、趨物等の繊維表面に活性炭酸粒子を酥着させることが出来る。

本発明のフィルターエレメントは、エレクトレットフィルターと吸着利含有フィルターを依属して、ブリーツ状に一体成形したものとする必要が ホス

破菌するとき、ブリーツ加工により一体成形出来る場合はそれでもよいが、少量のホットメルト接着剤を併用すれば、堅牢な一体成形が可能である。

ブリーツ加工は折り目をつけて熱板の間を通す 等の方法により実施することができる。その際、 エレクトレットフィルターと吸着剤または活性供 を舐着させたシートを重ねて同時にブリーツ加工 するのが好ましい。また、エレクトレットフィル ターと吸着剤または活性炭を付着させたシートが、 度が遠くなる。本実施例に示すようにヤシ殻を原料とした活性炭で、300 メッシュバスの成分が90 %、平均粒径が約20μmくらいのものが好適である。

吸着剤を含有せしめるシートの材質は特に限定しないが、プリーツ加工が出来る性質を有するものである必要がある。シートの組織は、編物、結物、不織布、ネット等が広く使用できる。また、プリーツ加工が出来る材質としては、例えば、ポガリエステル、ポリプロピレン、ナイロン等がが、プリエステル、ポリプロピレン、ナイロン等ががである。また、織り方や編み方は限定しないが、通気抵抗を下げるために、一定間隔で穴の開いている網目状生地が好ましい。

活性炭粒子をシートに含存させる方法は特に限定しないが、塩物等の繊維に添着させるためにはパインダーが必要である。しかして、パインダーによって活性炭表面が部分的に被覆されるため或る程度の吸着能力の低下は避け難いが、その機類により低下の度合いが異なる。一般に、懸濁している粒子の粒径が大きなラテックス系の接着剤を

-8-

すれるのを防ぐため、あらかじめ両者をホットメ ルト又はその他の接着剤で点接着しておく方法等 も適用することが出来る。

別々にブリーツ加工した後、これを接着して使用することもできる。また、吸着剤または活性炭を付着させたシートの表質両面にエレクトレットシートを重ねて使用することもできるし、何重かに砂層して使用してもよい。

ブリーツした後、形が崩れるのを防ぐため、高 分子材料又はその他の組状補強材で各山の頂点を 連結し、ブリーツのピッチが乱れないようにする ことも出来る。

本発明は空気清浄機に使用するためのフィルターエレメントである。前記のようにして、一体成 形したフィルターは空気清浄機のサイズに合わせ て、所要の大きさに栽断して装着される。空気清 浄機はとくに限定せず、ビルの室内用、家庭用、 堆内用等に使用するものが広く含まれる。

(作用・効果)

木発明は、エレクトレットフィルターと活性炭

シートを組み合わせることにより、たばこの紫色の屋の主成分である、径1μm以下の空気中の浮遊的しんの他、空気中の臭気を効率良く除去することが出来る。

また、圧損失が極めて低い特性を有するため、 大型の空気を循環させるのに適し、空気補浄機用 のフィルターエレメントに好適である。

更に、この獣層フィルターは一体成形されているため、コンパックトで、取扱も容易であり、この点においても、空気潜浄機用のフィルターエレメントとして好適である。

(実施例)

以下尖距例を挙げて木発明をさらに具体的に説明する。

本発明の実施例は以下のa、b、cの素材を用いて作成したフィルターエレメントを使用した。 素材 a エレクトレットフィルター

材質 ポリプロピレン、繊維径30μm、 厚さ 1 mm、目付100 g / ㎡、 プリーツ巾1 cm、1 cmの間のブリーツ山

- 11-

と同様の活性炭懸濁液に設強し、活性炭目付か150g/ 出となるように絞った後、 120 °Cで乾燥した。

实施例 1

素材 a を素材 b と同じ巾にブリーツし、素材 a と素材 b を少量のホットメルト接着剤で点接着して機関した。

その斜視図を取2図にしめす。また、第1級に 活性炭目付益と、エレメントの圧損失の関係を示 した。

活性炭目付量は、JIS N 8812「石炭類及びコークス類の工業分析法」に準じて測定し、圧損失は 1 m/sec の風速で、25℃で測定した。

エレメントの吸着性能を第1図に示す。吸着性能は、空気清浄装置運転時間と硫化水素ガスの残存率の関係で示した。その測定方法は下記のようである。

10 cm × 30 cm に数断したエレメントを、風速1m/sec のガスを処理できる空気情浄装置に装着して、予 め硫化水紫ガス濃度を1000ppm に網盤した1 ㎡ア 数は1ケ、ブリーツ後の長さは、元の長 さの2分の1である。

案材 b ネット状編み地に粉末循性炭を付着させ たもの

> ネット状編み地の材質・形状 100 dr ボリエステル糸を用いて目開き 3 mm、目 付50g/㎡に編んだもの。

> 通常の吸寄能力を持つ微粉末ヤシ殻活性炭100 部を水120 部に分散させ、接着 割として、2 96 CMC水溶液40部と、45% アクリロニトリルブタジエン系ラテックス260 部を加えた懸濁液を作り、上記ネット状編み地を懸濁液内に漫遊して、引き上げた後、絞って120 ℃で乾燥した。 「四ろ1.0 四活性炭目付100g/m

素材 c ポリウレタン発泡シートを用いたシート 状活性炭

> ポリウレタン発泡シートのセル抜き品 (1インチ間のセル数 8 ケ、3 ☎厚さ、 ポリウレタン目付80g/㎡)を、試料 b

> > - 12-

クリル製ポックス内にセットした。空気の循環時間と、残存硫化水素ガス濃度の関係を調べた。その結果を第1回に示す。

ガス設度測定は、PPD 検出器(Plame lonization Detector)付き高感度ガスクロを用いた。

空気術浄装優にエレメントを装着して、大気を 吸引し、吐出側での大気粉駆除去性能を調べたが、 客材 a との間に差は認められなかった。

比較例」

素材 a の後に素材 c をおいて、エレメントとした。活性炭目付益と、エレメントの圧損失の関係および、空気荷浄装置運転時間と硫化水素ガスの 残存率の関係を実施例 」と同様に測定した。その 結果を第1要および、第1図に示す。

比較例 2

素材 a の後にブリーツしてない素材 b を使いて、エレメントとした。活性炭目付量と、エレメントの圧損失の関係および、空気清浄装置運転時間と破化水索ガスの残存率の関係を実践的 1 と同様に制定した。その結果を第1表および第1関に示す。

表

	実路例 1	比較倒!	比較例 2
全体目付益 双/㎡	500	430	400
活性炎目付益 男/㎡	200	150	100
E 担 失 mmAq /枚	0. 9	1.0	1. 0

4. 図面の簡単な説明

第1図は、実施例1、比較例1及び2の空気前 **作装貨運転時間と硫化水素ガス段存率の関係を示** したものである。


- 1---实施例1
- 2 …比較例 1
- 3 ---比較例 2

第2図は本発明の一態様を示したもので、網状 の編み地に活性炭を付着したフィルターとエレク トレットシートと重ねて、一体にプリーツ成形し た脱典エレメントの斜视図である。

- . 4…活性炭循着シート
 - 5 …エレクトレットフィルター


クラレケミカル株式会社 頗 人 弁理士 小田中 吞雌 代 型 人

第1図



空気滑净装置運転時間

第 2 図



PUBLISHED UNEXAMINED PATENT APPLICATION

Published on Mar. 9, 1992

Title of The Invention:

FILTER ELEMENT FOR AIR-PURIFYING

Claim:

A filter element for air-purifying formed in pleats like shape by laminating and integrating a sheet-like electret filter and a sheet including a deodorizing adsorbent.